

H3452 Premium Photoluminescent Coarse Resilient Data Sheet

Subject	Test method
Composition	Composite construction
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.52mm
Tackloop (kg/25.4mm)	2.88
Cohesion (mins/25°C)	4320
Adhesion to steel (kg/25.4mm)	2.3
Temperature range	-10°C ~ 80°C
Maximum roll size	1220mmx50m
Life (months)	12 to 24
Glow Time	8~10 hours

The independent test laboratory at Adhesive Technical Services Ltd performed the temperature test, England (test results available)

Coefficient of Friction Data

	Dry Surface Test Result	Wet Surface Test Result
H3452 Coarse Resilient	95 TRL	60 TRL

	Coefficient of Friction Category	Test
H3452 Coarse Resilient	R10	DIN51130

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H3452 (Photoluminescent)			48.5	4

Photoluminescent data

Time	Luminance mcd/m ²	Test date
10 minutes	299	14/04/15
60 minutes	40	14/04/15

All the above data is for reference only.

©Heskins Ltd 1997-2024

