



ANTI-SLIP SOLUTIONS

mail@heskins.com

www.heskins.com

23/04/2024

H3454 Super Photoluminescent Coarse Resilient Data Sheet

Subject	Result
Composition	Composite construction
Type of adhesive	Solvent acrylic
Overall thickness (mm)	1.52mm
Tackloop (kg/25.4mm)	2.88
Cohesion (mins/25°C)	4320
Adhesion to steel (kg/25.4mm)	2.3
Temperature range	-10°C ~ 80°C
Maximum roll size	1220mmx50m
Life (months)	12 to 24
Glow Time	4 ~ 6 hours

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H3454 (Photoluminescent)			50.25	4

Coefficient of Friction Data

Test	Dry Surface Test Result	Wet Surface Test Result
H3454 Coarse Resilient	95 TRL	60 TRL

Test	Coefficient of Friction Category	Test
H3454 Coarse Resilient	R10	DIN51130

Photoluminescent Data

Time	Luminance mcd/m ²	Test date
10 minutes	138	14/04/15
60 minutes	18	14/04/15

DIN 67510

The above tests were conducted in accordance with Pendulum, the tests were conducted at a recognised independent friction testing laboratory, and copy certificates are available on request. Pendulum is a dynamic test, for static tests we also have results ASTM C 1028-96.

All the above data is for reference only.

©Heskins Ltd 1997-2024

