

H8I52 Premium Grade Egress Tape Data Sheet

Subject	Result
Composition	PET
Type of adhesive	Pressure sensitive
Overall thickness (mm)	0.37mm
Glow Time	8-10 Hours
Temperature range	-30°C ~ 90°C
Maximum roll size	1240mmx50m
Colour (Daylight)	Greenish Yellow
Glowing Colour	Bright green

The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of BS.8493:2008+A1:2010.

LRV Test Results

SKU (Colour)	RAL	Pantone	Av. LRV	Range
H8I52 (GID)	6019	365 U	96.3	3.2

Photo-Luminescent Performance*

Time	Luminance (mcd/m ²)	Test date
10 minutes	222	20/02/17
60 minutes	27	20/02/17

Decay time to 0.3 mcd/m² > 600 minutes

DIN 65710

The above tests were conducted in accordance with ASTM 2072. Test Method E 2073, shall be not less than: 20.0 mcd/m² at 10 min after activation has ceased; and 2.8 mcd/m² at 60 min after activation has ceased.

All the above data is for reference only.

©Heskins Ltd 1997-2024