



U GROUP SRL
Via Borgomanero n° 1
28040 Paruzzaro (NO)

LEGAL DATA:
C.F e Reg.Imp.Novara:02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 lv

CONTACTS:
WEBSITE: www.u-power.it/it
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 27/05/2024

DATA SHEET

PRODUCT PICTURE

RANGES

TECHNOLOGIES

SO10104 PREMIERE S3 SRC
Natural Confort 11 Mondopoint
AirToe Composite
SHOE TYPE "B"
SIZE RANGE 38-47 (UK: 5-12)
Size tested: 42 - WEIGHT Kg 1,359



STEP ONE



DESCRIPTION

TECHNICAL SPECIFICATIONS

EN ISO STANDARD

VALUE

Ankle boots safety shoes, U-Power, comfortable and breathable of the Step One range, with soft water-repellent grained leather upper with inserts in ultra-breathable Textile, composite toe cap, anti-puncture, anti-slip, ergonomic steel foil and PU/PU sole, S3 SRC

SAFETY TOE CAP "AirToe Composite"

Impact resistance. Free heights after collision mm
Compressive strength. Free heights after compr. mm

≥ 14
≥ 14

17,5
16,0

INSOLE "Classic steel midsole"

Puncture resistance N

≥ 1100

Compliant

ELECTRICAL RESISTANCE CATEGORY

Environmental class 1 - 12% humidity
Environmental class 2 - 25% humidity
Environmental class 3 - 50% humidity

10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)
10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)
10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)

< 10⁹ Ohm
< 10⁹ Ohm
< 10⁹ Ohm

UPPER DYNAMIC WATERPROOFING AFTER 60'

Water absorption after 60'
Water transmitted after 60'
Permeability to water vapor mg/(cm² h)
Permeability coefficient mg/cm²

≤ 30%
≤ 0.2 gr
≥ 0.8
≥ 15

14
0,1
3,2
27,1

VAMP LINING

Permeability to water vapor mg/(cm² h)
Permeability coefficient mg/cm²

≥ 2
≥ 20

4,7
42,5

Resistance to abrasion - DRY cycles

25600 cycles

No hole

Resistance to abrasion - WET cycles

12800 cycles

No hole

INSOLE

Abrasion resistance

≥ 400 cycles

No damage

SOLE WEAR

Abrasion resistance (volume loss) mm³
Bending resistance mm
Resistance to sole / midsole detachment N/mm
Hydrocarbons resistance (% volume variation)
Heel energy absorption J
Adherence coef. with EN 13207 SRB method
Adherence coef. with EN 13207 SRA method

≤ 150
≤ 4
≥ 3
≤ 12
≥ 20
≥ 0.18
≥ 0.32

56
2,3
4,1
3
40
0,20
0,38