



U GROUP SRL
Via Borgomanero n° 1
28040 Paruzzaro (NO)

LEGAL DATA:
C.F e Reg.Imp.Novara:02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 lv

CONTACTS:
WEBSITE: www.u-power.it/it
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 27/05/2024

DATA SHEET

PRODUCT PICTURE

RANGES

TECHNOLOGIES

UW20022 REBOUND GRIP S2 SRC
Natural Confort 11 Mondopoint
AirToe Composite
SHOE TYPE "A"
SIZE RANGE 35-47
Size tested: 42 - WEIGHT Kg 0,889



WHITE68&BLACK



DESCRIPTION

TECHNICAL SPECIFICATIONS

EN ISO STANDARD

VALUE

White low safety shoes, U-Power, comfortable and light of the White68 & Black range, with New Safety Dry water-repellent and breathable microfiber upper, resistant to bacteria and organic chemical residues, easily washable, AirToe Composite tip, non-slip and PU / PU sole U-Grip 68, S2 SRC

SAFETY TOE CAP "AirToe Composite"

Impact resistance. Free heights after collision mm ≥ 14
Compressive strength. Free heights after compr. mm ≥ 14

INSOLE "Not present"

Puncture resistance N ≥ 1100

ELECTRICAL RESISTANCE CATEGORY

Environmental class 1 - 12% humidity $10^5 \Omega$ e $10^9 \Omega$ (0,1 M Ω a 100 M Ω) $< 10^9$ Ohm
Environmental class 2 - 25% humidity $10^5 \Omega$ e $10^9 \Omega$ (0,1 M Ω a 100 M Ω) $< 10^9$ Ohm
Environmental class 3 - 50% humidity $10^5 \Omega$ e $10^9 \Omega$ (0,1 M Ω a 100 M Ω) $< 10^9$ Ohm

UPPER DYNAMIC WATERPROOFING AFTER 60'

Water absorption after 60' $\leq 30\%$ 14
Water transmitted after 60' ≤ 0.2 gr 0.1
Permeability to water vapor mg/(cm² h) ≥ 0.8 7,2
Permeability coefficient mg/cm² ≥ 15 64,4

VAMP LINING

Permeability to water vapor mg/(cm² h) ≥ 2 4,7
Permeability coefficient mg/cm² ≥ 20 42,5
Resistance to abrasion - DRY cycles 25600 cycles No hole
Resistance to abrasion - WET cycles 12800 cycles No hole

INSOLE

Abrasion resistance ≥ 400 cycles No damage

SOLE WEAR

Abrasion resistance (volume loss) mm³ ≤ 150 34
Bending resistance mm ≤ 4 1,4
Resistance to sole / midsole detachment N/mm ≥ 3 3,4
Hydrocarbons resistance (% volume variation) ≤ 12 3,5
Heel energy absorption J ≥ 20 35
Adherence coef. with EN 13207 SRB method ≥ 0.18 0,29
Adherence coef. with EN 13207 SRA method ≥ 0.32 0,62

20345:2011

RESULT