



U GROUP SRL
Via Borgomanero n° 1
28040 Paruzzaro (NO)

LEGAL DATA:
C.F e Reg.Imp.Novara:02041920030
CCIAA Novara REA: 211799
P.IVA: IT02041920030
Codice Export: No015724
Cap.Soc.: 119.000 lv

CONTACTS:
WEBSITE: www.u-power.it/it
EMAIL: info@u-power.it
TEL: +39 0322 53 94 01
FAX: +39 0322 23 00 01

REV. 27/05/2024

DATA SHEET

PRODUCT PICTURE

RANGES

TECHNOLOGIES

BC20315 TUDOR S1P SRC
Natural Confort 11 Mondopoint
Steel toe cap
SHOE TYPE "A"
SIZE RANGE 35-47 (UK: 2-12)
Size tested: 42 - WEIGHT Kg 1,161



STYLE&JOB



DESCRIPTION

TECHNICAL SPECIFICATIONS

EN ISO STANDARD

VALUE

Low safety shoes, U-Power, classic and strong of the "Style & Job" range, with suede leather upper with ultra breathable Textile inserts, steel toe cap, anti-puncture, anti-slip, ergonomic steel foil and PU / PU sole, S1P SRC

SAFETY TOE CAP "Steel toe cap"

Impact resistance. Free heights after collision mm
Compressive strength. Free heights after compr. mm

20345:2011

RESULT

≥ 14 17,0
≥ 14 18,5

INSOLE "Classic steel midsole"

Puncture resistance N

≥ 1100 Compliant

ELECTRICAL RESISTANCE CATEGORY

Environmental class 1 - 12% humidity 10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)
Environmental class 2 - 25% humidity 10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)
Environmental class 3 - 50% humidity 10⁵ Ω e 10⁹ Ω (0,1 MΩ a 100 MΩ)

< 10⁹ Ohm
< 10⁹ Ohm
< 10⁹ Ohm

UPPER DYNAMIC WATERPROOFING AFTER 60'

Water absorption after 60' ≤ 30%
Water transmitted after 60' ≤ 0.2 gr
Permeability to water vapor mg/(cm² h) ≥ 0.8
Permeability coefficient mg/cm² ≥ 15

N.A.
N.A.
6,4
55,1

VAMP LINING

Permeability to water vapor mg/(cm² h) ≥ 2
Permeability coefficient mg/cm² ≥ 20
Resistance to abrasion - DRY cycles 25600 cycles
Resistance to abrasion - WET cycles 12800 cycles

24,7
197,9
No hole
No hole

INSOLE

Abrasion resistance ≥ 400 cycles

No damage

SOLE WEAR

Abrasion resistance (volume loss) mm³ ≤ 150
Bending resistance mm ≤ 4
Resistance to sole / midsole detachment N/mm ≥ 3
Hydrocarbons resistance (% volume variation) ≤ 12
Heel energy absorption J ≥ 20
Adherence coef. with EN 13207 SRB method ≥ 0.18
Adherence coef. with EN 13207 SRA method ≥ 0.32

80
2,0
4,4
3
26
0,19
0,40